



A review on photocatalytic, antimicrobial, cytotoxic and other biological activities of phyto-fabricated copper nanoparticles

Wali Muhammad, Bilal Haider Abbasi*, Syed Salman Hashmi, Muhammad Haroon, Muzamil Shah

Department of Biotechnology, Quaid-i-Azam University Islamabad 45320, Pakistan

Key words: Copper nanoparticles, Green synthesis, Characterization, Antimicrobial activity, Disease organizations.

<http://dx.doi.org/10.12692/ijb/13.1.320-337>

Article published on July 30, 2018

Abstract

Since its advent, nanotechnology has become an indispensable area of research and innovation, introducing revolutionary changes in current research areas like engineering, medical sciences, drug discovery and formulations, optoelectronics and biosensors. Metallic nanoparticle synthesis has become a requisite of modern experimentation however, much of the research involves either silver or gold nanoparticles. Considering the fact, it is imperative to explore the potentials of other metallic nanoparticles as well. Current review focuses on exploration of potentials of Copper nanoparticles in various domains of research. The review highlights common synthesis methods of Copper nanoparticle synthesis and the superiority of green route over other approaches. Characterization techniques and multifarious biological potentials of Copper nanoparticles have also been reviewed. Researchers have recognized green synthesis route as the best alternative to traditional methods utilized for synthesizing copper nanoparticles. Green synthesized Copper nanoparticles have also been found to have superior antioxidant, antimicrobial, antifungal, cytotoxic and photocatalytic potentials. As of now, the exact mechanism behind synthesis and biological activities of Copper nanoparticles is not known. Identification of the exact mechanism can revolutionaries the discipline of nanotechnology.

* **Corresponding Author:** Bilal Haider Abbasi ✉ bhabbasi@qau.edu.pk

Introduction

The domain of nanotechnology has emerged from established areas of science like physics, chemistry, biology and engineering sciences. Nanotechnology involves intervention of novel strategies with the help of which atoms and small particles are manipulated. Nanoparticles (NPs), the key product of nanotechnology, are particles having dimensions ranging from 1–100 nm (Farias, Silva *et al.* 2014). The properties of NPs show immense variations to those of bulk materials due to their extremely small size (Petit, Lixon *et al.* 1993, Kaviya, Santhanalakshmi *et al.* 2011). With the advancement in nanotechnology, size controlled synthesis of nanoparticles can be carried out to furnish NPs that possess properties suiting a particular purpose. The properties that NPs possess are due to two core reasons, novel quantum impact and increased surface to volume ratio. As compared to their bulk counterparts, the pre-eminent surface to volume proportions in NPs imitates enhanced catalytic reactivity. Likewise such small dimensions of NPs signifies the influence of quantum impact on quality and properties of material (Hewakuruppu, Dombrowsky *et al.* 2013). Since its dawn, NPs have dominated different areas of science. The use of NPs have been reported in areas like catalysis; (Husen and Siddiqi 2014), Photonics; (Ren, Hu *et al.* 2009, Ahamed, Alhadlaq *et al.* 2014), gadgets; (Kamal, Khan *et al.* 2016), bio labeling; (Chen, Wang *et al.* 2012), detection; and surface upgraded Raman Scattering; (Cioffi, Torsi *et al.* 2005, Abboud, Saffaj *et al.* 2014, Ahamed, Alhadlaq *et al.* 2014, Sutradhar, Saha *et al.* 2014, Naika, Lingaraju *et al.* 2015), drug delivery (Longano, Ditaranto *et al.* 2012, Wali, Sajjad *et al.* 2017), etc. Copper Nanoparticles (Cu-NPs) have caught the eye of scientists lately owing to their biocidal properties and numerous applications in wound dressings (Giannousi, Avramidis *et al.* 2013, Kanhed, Birla *et al.* 2014, Shende, Ingle *et al.* 2015, Bramhanwade, Shende *et al.* 2016). Modern technologies like catalytic process, gas sensors, solar cells and high temperature super-conductors have also benefitted from Cu-NPs (Schilling, Bradford *et al.* 2010, Song, Vijver *et al.* 2015). This review

climaxes green synthesis of Cu-NPs and describes how to characterize, and what are different activities of these used NPs.

Copper Nanoparticles (CuNPs)

Biosynthesis of Copper Nanoparticles (CuNPs)

Researchers in antecedent decades were hell bent on exploring greener and safer synthesis approaches for Nano metallic particles (Raveendran, Fu *et al.* 2003, Iravani and Zolfaghari 2013, Mittal, Chisti *et al.* 2013) with significant focus on methods that involved microorganisms (Mandal, Bolander *et al.* 2006) and other biological beings other than plants and plants extract (Thakkar, Mhatre *et al.* 2010). Plants and plant material based synthesis approaches were not properly explored. It wasn't until recent decade when researchers realized the potential of plants for metallic NP synthesis and the plethora of advantages that it has to offer, the foremost being circumvention of need to maintain cell cultures. An added advantage of utilizing plants as factories for NP synthesis is bypassing the chances of pathogenicity. This review describes the plant and plant extract methods so as to optimize the most appropriate method for the synthesis of Cu-NPs. The general scheme of synthesis route is shown in Figure 1.

Extracts from a variety of plants have been used for preparing Cu-NPs with diverse range of sizes and shapes owing to the nature of extract and synthesis conditions. Cu-NPs are highly oxidant in nature that gives rise to unforeseen issues related to NP stability, aggregation and oxidation resistance. This hindered the focus on Cu- NPs synthesis as compared to other metals initially. Later on (Pedersen, Wang *et al.* 2008) it was concluded that Cu-NPs are oxidized only upon the surface at room temperature. NPs like gold and silver on the other hand (Rafique, Shaikh *et al.* 2017) are much better in withstanding oxidation as compared to Cu. Still, Cu-NPs synthesis can be an attractive contender for nano based research owing to its copiousness and inexpensiveness. With development in nanotechnology, aggregation and oxidation issues can also be addressed conveniently through capping agents like polymers (Balogh and

Tomalia 1998, Crooks, Zhao *et al.* 2001) and natural ligands.

The best solution in practice these days is synthesis of Cu-NPs by utilizing plants and plant based products that can serve as both capping and reducing agents. S. Renganathan *et al.*, demonstrated the plant based synthesis approach for Cu-NPs by using *Capparis zeylanica* leaf extract. CuSO₄ solution was used as precursor salt while the leaf extract served as reducing agent for NP synthesis. The reaction was carried out for 12 h which resulted in Cu-NPs with cubical shape and size ranging from 50–100 nm. The antimicrobial potential of Cu-NPs was investigated against pathogenic bacterial strains including *Escherichia coli*, *Staphylococcus aureus* and *Pseudomonas aeruginosa* (Subhankari and Nayak 2013). Shende *et al.*, studied that *Citrus medica* Linn fruit extract can be used to reduce the CuSO₄ solution (Shende, Ingle *et al.* 2015). The synthesized nanoparticles were crystalline in nature with size range 20nm. The synthesized NPs showed good antimicrobial activities. (Shende, Ingle *et al.* 2015) Angrasan & Subbaiya carried out that *Vitis vinifera* leaves extract can be used to reduce the CuSO₄ solution. The synthesized NPs were characterized by UV-Vis and FTIR. The established nanoparticles showed potential anti-microbial activity against *Escherichia coli*, *Staphylococcus aureus*, *Pneumonia*, *Salmonella typhi* and *Bacillus subtilis* (Angrasan and Subbaiya 2014). G. Caroling *et al.*, elaborated that *Guava* fruit extract has the potential to reduce the CuSO₄ solution. The prepared NPs were spherical in shape with size range 15-30nm. These prepared NPs showed anti-microbial activity against *Escherichia coli*, *Staphylococcus aureus* (Rafique, Shaikh *et al.* 2017). Kala, A *et al.*, illustrated the production of Cu-NPs using *Datura innoxia*. The leaves extract of this plant were used which synthesized spherical NPs with the size of 5-15nm. These prepared NPs showed potential activity against rice pathogens (Kala, Soosairaj *et al.* 2016). Gopinath *et al.*, synthesized Cu-NPs using leaf extract of *Nerium Oleander*. He and his fellows mentioned that these NPs have great potential to reduce CuSO₄ solution. The synthesized

NPs were characterized by different techniques and hence showed that NPs are spherical in shape. The established NPs showed good bacterial activity against five different organism like *Salmonella typhi*, *Klebsiella Pneumonia*, *Escherichia coli*, *Staphylococcus aureus* and *Bacillus subtilis* (Gopinath, Subbaiya *et al.* 2014). Saranyaadevi *et al.*, carried out that *Capparis zeylanica* leaf extract can be used to reduce the CuSO₄ solution. The prepared NPs were characterized by UV-visible spectroscopy, FTIR, XRD, SEM, EDX and TEM. The study showed that the synthesized NPs were cubical in shape and with the size range from 50-100nm. The synthesized NPs showed high bacterial activity against *Staphylococcus aureus*, *Pseudomonas aeruginosa* and *Escherichia coli* (Saranyaadevi, Subha *et al.* 2014). M Jayandran *et al.*, produced CuNPs using leaf extract of *Curcumin*. The synthesized NPs showed potential to reduce copper oxide. The prepared NPs characterized through techniques of UV-visible spectroscopy, XRD, TEM. The synthesized nanoparticles showed that its average size is 60-100nm. The NPs were found both in cubic and rod shape. This study also showed potential bacterial activity against *Staphylococcus aureus*, *Bacillus subtilis*, *Escherichia coli*, *Staphylococcus Bacillus* (Jayandran, Haneefa *et al.* 2015).

Subbaiya and MasilamaniSelvam also reported plant based Cu NP synthesis using *Hibiscus rosa-sinensis* leaf extract as reducing agent. CuNO₃ was used as precursor salt and the mixture of salt solution and plant extract was kept for 48 h in dark. The resulting Cu-NPs were spherical in nature and showed great potential as antimicrobial agent against pathogenic *Bacillus subtilis* and *E. coli*. The study concluded that the Cu-NPs produced may serve as efficient drug for lung cancer therapy (Rafique, Shaikh *et al.* 2017).

Harne, S *et al.*, carried out that latex of *Calotropis procera* L. can be used to reduce the Cu (CH₃COO)₂ solution. These NPs were synthesized and were characterized through the techniques of XRD, FTIR, TEM and EDX. This study showed that established NPs are polydispers spherical in shape and also presented that its average is 15±1.7nm. Cytotoxicity

studies showed excellent viability at 120 μM concentration of copper nanoparticles (Harne, Sharma *et al.* 2012).

Correspondingly, many other plants and their extracts were used to synthesize the Cu-NPs. A

comprehensive study is given in Table 1,2,3,4, which describes varied characterization techniques and also shows different activities of each Cu-NPs.

Table 1. Photocatalytic degradation of various harmful dyes through Biosynthesized Cu-NPs.

| Plant | Part used | Size | Morphology | Characterization | Activity | Ref |
|-------------------------------|-----------|-------------------|------------------------|---|--|--|
| <i>Euphorbia esula L</i> | Leaves | 20–110nm | Spherical | UV-visible spectroscopy, XRD, FTIR and TEM | Catalytic activity in the reduction of 4-NP at room temperature in aqueous medium | (Nasrollahzadeh, Sajadi <i>et al.</i> 2014) |
| <i>Thymus vulgaris L.</i> | Leaves | 56 nm | Spherical | UV spectrum, FTIR, XRD, FESEM, EDS, TEM, SEM | Excellent catalytic activity, convenient reusability and long-term stability | (Issaabadi, Nasrollahzadeh <i>et al.</i> 2017) |
| <i>Azadirachta indica</i> | - | - | - | UV-Vis spectroscopy, FTIR, TEM | Excellent catalytic activity in the presence of NaBH_4 . | (Thirumurugan, Harshini <i>et al.</i> 2017) |
| <i>Fortunella japonica</i> | Fruit | 5-10 nm | Spherical | UV-Vis spectroscopy, AFM, HR-TEM, XRD, Raman spectroscopy, FTIR | Act as a catalyst and showed good degradation percentage of 4-NP pollutant | (Singh, Kumar <i>et al.</i> 2017) |
| <i>Banana</i> | Peel | 60 nm | Spherical | XRD, EDX, FE-SEM, FTIR, UV-Vis spectroscopy | Photo catalytic activity, degradation of Congo red (CR) under direct sunlight | (Aminuzzaman, Kei <i>et al.</i> 2017) |
| <i>Abutilon indicum</i> | Leaves | 16.78 nm | Spherical | XRD, EDX, SEM, UV-Vis spectroscopy | Good photo-catalytic, antimicrobial and antioxidant activities. | (Ijaz, Shahid <i>et al.</i> 2017) |
| <i>Rheum palmatum L.</i> | Root | 10–20 nm | Spherical | UV-Vis spectroscopy, FTIR, SEM, XRD, TEM | Catalytic activity for reduction of 4-NP, MB, and RhB | (Bordbar, Sharifi-Zarchi <i>et al.</i> 2017) |
| <i>Centella asiatica (L.)</i> | Leaves | 2-5 μm | - | UV-Vis spectroscopy, SEM, IR spectroscopy and EDX | Used as catalyst for photocatalytic degradation of methyl orange (Organic pollutant) | (Devi and Singh 2014) |
| <i>Broccoli</i> | - | ~4.8 nm | Spherical | UV-Vis, FTIR, TEM, DLS, XRD and cyclic voltammetry | High catalytic activity against 4-NP | (Prasad, Kanchi <i>et al.</i> 2016) |
| <i>Cavendish banana</i> | Peel | 91.0 nm | Irregular and dumbbell | XRD, SEM, FT-IR, EDX and PSA | Photocatalytic activity/ degradation of red and green dye | (Leong 2016) |
| <i>Euphorbia prolifera</i> | Leaves | 5–17 nm | Spherical | FESEM, EDS, elemental mapping, TEM and XRD | Excellent catalytic activity for the degradation of MB and CR in the presence of NaBH_4 | (Momeni, Nasrollahzadeh <i>et al.</i> 2016) |

Potential Applications of Copper Nanoparticles (Cu-NPs)

Cu-NPs have attracted several researchers owing to their catalytic and optical properties (Nasrollahzadeh, Sajadi *et al.* 2015) as well as their applications in engineering domains like electrical technology and mechanics (Kim, Lim *et al.* 2008, Salavati-Niasari, Davar *et al.* 2008). Cu NPs are imperative locum tenens for other NPs like silver, gold and platinum due to their applicability in thermal conducting materials and microelectronics (Eastman, Choi *et al.*

2001, Lu, Sui *et al.* 2001). When it comes to plant extract based NPs, the synthesized nanoparticles have added advantage of possessing medicinal properties acquired from capping agents present in plant extract. This enhances their potential applications in targeted drug delivery, medication, and cosmetics (Rafique, Shaikh *et al.* 2017). The antibiotic potential of Cu-NPs have paved the way for their applications in wound dressings, (Borkow and Gabbay 2009, Rubilar, Rai *et al.* 2013) while on industrial level, Cu NPs have been used in solar cells, gas sensors, (Atarod,

Nasrollahzadeh *et al.* 2015, Nasrollahzadeh, Maham *et al.* 2015) superconductors with tolerance for high temperature and catalytic process (Carnes and Klabunde 2003, Li, Liang *et al.* 2008, Yuhas and Yang 2009). Cu-NPs because of their brilliant physical properties are used in antibiotics. The stability of Cu NPs upon matrix and their disincentive and bactericidal properties makes them suitable candidates for coating the equipment used in

hospitals, (Li and Peterson 2006) antimicrobial materials, (Wang, Chen *et al.* 2002, Guduru, Murty *et al.* 2007) super strong materials, (Male, Hrapovic *et al.* 2004, Kang, Mai *et al.* 2007) sensors (Vukojević, Trapp *et al.* 2005, Xu, Zhao *et al.* 2006, Kantam, Jaya *et al.* 2007) and catalysts. (Athanassiou, Grass *et al.* 2006, Pecharromán, Esteban-Cubillo *et al.* 2006, Rodriguez, Liu *et al.* 2007).

Table 2.Antibacterial activities of Biosynthesized Cu NPs.

| Plant | Part used | Size | Morphology | Characterization | Activity | Ref |
|-----------------------------|-----------|------------|-------------------|---|---|--|
| <i>Vitis vinifera</i> | Leaves | - | - | UV-Vis spectroscopy and FTIR | Anti-microbial activity against <i>E. coli</i> , <i>S. aureus</i> , <i>pneumonia</i> , <i>S. typhii</i> and <i>B. subtilis</i> | (Angrasan and Subbaiya <i>et al.</i> 2014) |
| <i>Nerium Oleander</i> | Leaves | - | - | UV-Vis spectroscopy and FTIR | Good bacterial activity against <i>S. typhii</i> , <i>K. Pneumonia</i> , <i>E. coli</i> , <i>S. aureus</i> and <i>B. subtilis</i> | (Gopinath, Subbaiya <i>et al.</i> 2014) |
| <i>Capparis zeylanica</i> | Leaves | 50–100 nm | Cubical Structure | UV-Vis spectroscopy, FTIR, SEM, EDX and TEM | Bacterial activity against <i>S. aureus</i> , <i>P. aeruginosa</i> and <i>E. coli</i> | (Saranyaadevi, Subha <i>et al.</i> 2014) |
| <i>Curcumin</i> | Leaves | 60- 100 nm | Cubic and Rods | UV-Vis spectroscopy, XRD, TEM | Bacterial activity against <i>S. aureus</i> , <i>B. subtilis</i> and <i>E. coli</i> | (Jayandran, Haneefa <i>et al.</i> 2015) |
| <i>Magnolia Kobus L.</i> | Leaves | 37–110nm | Spherical | UV-Vis spectroscopy, Inductively Coupled Plasma spectrometry (ICP), EDS, XPS, and HRTEM | Bacterial activity against <i>E. coli</i> | (Lee, Song <i>et al.</i> 2013) |
| <i>Malva sylvestris</i> | Leaves | 14 nm | Crystalline | UV-Vis spectroscopy, FTIR, SEM, XRD | Antibacterial activity against <i>Shigella</i> and <i>listeria</i> bacteria | (Awwad, Albiss <i>et al.</i> 2015) |
| <i>Aloe vera</i> | Leaves | 20–30 nm | Spherical | UV-Vis spectra, TEM, SEM, XRD, EDS | Antibacterial activity against fish bacterial pathogens | (Kumar, Shameem <i>et al.</i> 2015) |
| <i>Garcinia mangostana</i> | Leaves | 20–25 nm | Spherical | TGA, SEM, XRD, TEM, DTA | Highly antibacterial against <i>E. coli</i> and <i>S. aureus</i> . | (Prabhu, Rao <i>et al.</i> 2015) |
| <i>Ocimum sanctum</i> | Leaves | 79 nm. | Spherical | SEM, XRD, TEM, FTIR | Showed good antibacterial activity against <i>E-coli</i> bacteria | (Sadanand, Rajini <i>et al.</i> 2016) |
| <i>Terminalia bellirica</i> | Fruit | 2–7 nm. | Spherical | UV-Vis spectrophotometry, HRTEM, XRD, TGA | Antibacterial activity against <i>E.coli</i> | (Sadanand, Rajini <i>et al.</i> 2016) |
| <i>Citrus medica</i> | Fruit | 20nm | Crystalline | UV-Vis spectrophotometry, NTA and XRD | Antibacterial activity against <i>E.coli</i> and <i>K. pneumonia</i> | (Shende, Ingle <i>et al.</i> 2015) |

The small size of NPs adds to the bactericidal potential of NPs. The reactivity of Cu-NPs is also enhanced owing to its high surface to volume ratio allowing facile and close interaction with other membranes of microorganisms with high ratio (Narayanan and El-Sayed 2004). The antimicrobial potency of NPs is enhanced due to the fact that metal ions are released in colloidal solution. The colloidal solution of Cu-NPs had been reported to possess considerable antimicrobial potential when compared with standard antibiotics like chloramphenicol. Their potency as replacement for standard antibiotics was

evident against several bacterial and fungal strains studied by different researches (Ramyaadevi, Jeyasubramanian *et al.* 2012, Rafique, Shaikh *et al.* 2017). Dispersed CuNPs with size ranging between 2–5 nm have been reported to possess good antibacterial potential with the capacity to retrench microbial concentration by as much as 99.9% (Wang, Chen *et al.* 2002). Implantation of Cu NPs having around 6 nm diameter in films of polyvinyl methyl ketone showed that development of microbial colonies was clearly inhibited (Guduru, Murty *et al.* 2007). The floor functionalization of these particles with cur

cumin can also provide any other method for utilizing the curcuminoids toward practicable medicine transportation and therapeutics. (Jayandran, Haneefa *et al.* 2015) Various *in-vitro* techniques including the disk diffusion technique has been extensively used to elucidate the potential of Cu-NPs as antibacterial agents against plethora of bacterial strains and phyto pathogenic fungi. Several reports are present on inhibitory effects of Cu NPs against human pathogenic microbial strains like *E.coli*, *K. pneumoniae*, *P. aeruginosa*, *Propionibacterium*

acnes and *Salmonella typhi*. Inhibition of fungal strains infecting plants like *Fusarium culmorum*, *F. oxysporum* and *F. graminearum* have also been reported (Shende, Ingle *et al.* 2015). Both copper and Silver NPs have been extensively studied for their bactericidal applications by implanting these NPs on suitable support like carbon, polymers, polyurethane foam and sepiolite (Li, Lee *et al.* 2006). Yoon reported efficient antibiotic potential of Cu-NPs in a comparative study with silver NPs against *E.coli* and *B. subtilis* (Yoon, Byeon *et al.* 2007).

Table 3. Cytotoxic and Anticancer Potency of Biosynthesized Cu NPs.

| Plant | Part used | Size | Morphology | Characterization | Activity | Ref |
|----------------------------------|-----------|----------------------|----------------------------------|---|---|---|
| <i>Calotropis procera L.</i> | Latex | 15±1.7 nm | Polydisperse spherical | XRD, FTIR, TEM and EDAX | Cytotoxicity Studies showed excellent viability at 120 µM concentration of Cu NPs | (Harne, Sharma <i>et al.</i> 2012) |
| <i>Eclipta prostrata</i> | Leaves | 31±1.2 nm | Spherical, hexagonal and cubical | UV-Vis spectra, FTIR, XRD, HRTEM, SEM | Have high antioxidant and cytotoxic activity | (Chung, Abdul Rahuman <i>et al.</i> 2017) |
| <i>Ormocarpum cochinchinense</i> | Leaves | 2 µm and 1µmin | Cluster structure | UV-Vis Spectroscopy, FTIR, XRD, SEM, TEM, SAED | Significant cytotoxicity effect on human colon cancer | (Gnanavel, Palanichamy <i>et al.</i> 2017) |
| <i>Prosopis cineraria</i> | Leaves | 18.9 to 32.09 nm | Spherical | UV-Vis absorbance, FTIR, XRD, FESEM, and EDX | Antimicrobial and anticancer activity | (Jinu, Gomathi <i>et al.</i> 2017) |
| <i>Black bean</i> | Seed | ~26.6 nm | Spherical | XRD, FT-IR, XPS, Raman spectroscopy, DLS, TEM, SAED, SEM, and EDX | Significant activity to reduce cervical carcinoma colonies | (Nagajyothi, Muthuraman <i>et al.</i> 2017) |
| <i>Acalypha indica</i> | Leaves | 26–30 nm | Spherical | UV-Vis spectroscopy, XRD, FT-IR, SEM and EDX | Antimicrobial effect against <i>E. coli</i> , <i>P. fluorescence</i> and <i>C. albicans</i> . Potency against MCF-7 human breast cancer cell line | (Sivaraj, Rahman <i>et al.</i> 2014) |
| <i>Solanum tuberosum</i> | Starch | 54 nm | Spherical | UV-Vis spectrophotometry, XRD, SEM | Antimicrobial activity, anticancer properties against standard strains and MCF-7 cell line | (Alishah, Pourseyedi <i>et al.</i> 2017) |
| <i>Coleus aromaticus</i> | Leaf | 17-40nm and 21-48 nm | Spherical | HR-TEM, XRD, EDS, DLS, FTIR, FESEM | An efficient platform for intracellular mi-RNAs delivery and improving therapeutic outcomes for lung cancer. | (Wu, Wang <i>et al.</i> 2017) |

The application of both of these NPs as disinfectants in clinical wastewater containing contagious microorganisms have also been reported (Lin, Vidic *et al.* 1996, Yu-sen, Vidic *et al.* 1998). Zain reported improved antibacterial efficacy in case of Ag-Cu bimetallic NPs as compared to Ag and Cu NPs alone (Zain, Stapley *et al.* 2014). The alloys of Copper NPs have been reported for their applications in catalysis process like gas detoxification water gas shift catalysts (Barrabés, Just *et al.* 2006, Bracey, Ellis *et al.* 2009). Changes in surface properties, conformation and size

of NPs may aid in controlling catalytic properties of NPs (Niu and Crooks 2003, Hoover, Auten *et al.* 2006). High yield even in mild reaction conditions is main reason for popularity of Cu NPs in comparison to traditional catalysts (Phong, Khuong *et al.* 2011).

Characterization of Copper Nanoparticles

Several techniques can be used for the characterization of synthesized nanomaterial. Some of the most common characterization tools are UV-Visible Spectroscopy (UV-vis), Fourier transform

infrared spectrum analysis (FTIR), X-ray diffraction (XRD), Scanning electron microscopy (SEM) and transmission electron microscopy (TEM).

UV-Visible Spectroscopy (UV-Vis): A variety of metallic salt precursors have been used for synthesis of numerous NPs through different methods.

Literature shows that NP synthesis process usually takes 24 hours. Following the completion of reaction, different nanoparticles give SPR (Surface Plasmon Resonance) bands e.g. Cu NPs peaks can be observed between 200-800nm. These peaks can be efficiently measured using UV-Vis spectroscopy (Shobha, Moses *et al.* 2014).

Table 4. Miscellaneous biomedical applications of Biosynthesized Cu-NPs.

| Plant | Part used | Size | Morphology | Characterization | Activity | Ref |
|------------------------------|-------------|-----------|------------------------|--|--|--|
| <i>Commelina nudiflora</i> | Whole plant | 45-100 nm | Spherical | UV-Vis spectrophotometer, FESEM, EDX, XRD | Strong antioxidant, antifungal and antibacterial activity | (Kuppusamy, Ilavenil <i>et al.</i> 2017) |
| <i>Cassia auriculata</i> | Leaf | 23 nm | Spherical, polydispers | UV-Vis, EDS, SEM, TEM and DLS | Drug delivery vehicle for anti-rheumatic agents. | (Shi, Tang <i>et al.</i> 2017) |
| <i>Rubus glaucus</i> | Fruit/ Leaf | 43.3 nm | Spherical | UV-Vis spectrophotometry, TEM, SAED, XRD | DLS, Antioxidant potency evaluated against DPPH | (Kumar, Smita <i>et al.</i> 2015) |
| <i>Carica papaya</i> | Leaf | ~150 nm | Star-like structure | UV-Vis, SEM, TEM, HR-TEM, EDX, XRD | Water purification, degrade chlorpyrifos in water | (Rosbero and Camacho 2017) |
| <i>Cissus quadrangularis</i> | Leaf | 30 ± 2 nm | Spherical | UV-Vis spectroscopy, SEM, TEM, EDAX | XRD, FTIR, Anti-fungal activity against <i>A. niger</i> and <i>A. flavus</i> | (Devipriya and Roopan 2017) |
| <i>Saraca indica</i> | Leaf | 40-70 nm | Spherical | UV-Vis, FTIR, XRD, EDX, SEM, TEM and HRTEM | XPS, Applications in fluorescence emitting materials. | (Prasad, Patra <i>et al.</i> 2017) |
| <i>Eichhornia crassipes</i> | Leaf | 28 ± 4 nm | Spherical | UV-Vis spectroscopy, FESEM, EDX | FTIR, Highest inhibitory effect against fungal pathogens | (Vanathi, Rajiv <i>et al.</i> 2016) |
| <i>Punica granatum</i> | Peel | 40 nm | Spherical | UV-Vis spectroscopy, XRD | FTIR, SEM, Mortality efficacy against green peach Aphid | (Ghidan, Al-Antary <i>et al.</i> 2016) |

The formation of NPs can be monitored by observing the changes in peak formation with increasing time or increasing concentration of reactants (Precursor salt or Biological extract), each effecting the UV-vis absorption spectrum as the reaction proceeds and concentration of NPs increase (Yin, Wu *et al.* 2005, Swarnkar, Singh *et al.* 2011, Abboud, Saffaj *et al.* 2014).

The X-ray diffraction (XRD) Analysis: XRD is the most widely used technique for studying the metallic nature of NPs. This is done by analyzing the unit cell for its translational symmetry, shape and size.

The electron density within the unit cell can also be studied using XRD. All this information can be gathered from peak locations generated through XRD. The peak intensities are also used for specifically identifying the location of atoms (Shobha, Moses *et al.* 2014).

Fourier Transform Infrared

(FTIR) Spectroscopy: FTIR spectroscopic analysis is carried out to record the infrared intensity against the wavelength of emitted light. When it comes to nanoparticles, FTIR is a useful tool for identifying the nature of functional groups present in biological extracts that took part in capping and reduction of synthesized NPs.

The spectra obtained through FTIR provides the details of optical properties of NPs that may include the extinction cross-section, resonance wavelength and the scattering to absorption ratio (Shobha, Moses *et al.* 2014).

Microscopic techniques: Microscopic techniques are used to identify the morphological features of NPs. The micrographic image obtained using these techniques unfolds details about the shape and size of metallic nano particles in the series (Subhankari and

Nayak 2013). SEM image also reveals the details about uniformity of NP size and shape and aggregation state of NPs (Shobha, Moses *et al.* 2014).

Energy dispersive X-ray: EDX, also known as energy dispersive X-ray analysis (EDXA) is used for elemental analysis or composition of different elements in a sample. During EDX, a beam of electrons are focused upon the sample resulting in emission of X-rays. The X-rays emitted are then analyzed qualitatively and quantitatively.

Quantitative analysis involves identification of elemental concentration in a sample by analyzing the peak intensities while qualitative analysis, involves identification of different X-ray peaks and their positions specified within the spectrum.

Elements with atomic numbers ranging from 4-92 can be easily detected through EDX. Since the number of emitted X-rays is in direct proportion with elemental concentration of each element in sample (Shobha, Moses *et al.* 2014).




Fig. 1. Biosynthesis of Nanoparticles (NPs).

Antimicrobial activity of copper nanoparticles

This section deals with antimicrobial activity studies conducted using different concentrations of copper nanoparticles against human pathogenic bacteria belonging to various genera and species. Using 100 ml of copper oxide nanoparticles of 46 nm synthesized by *Tabernaemontana divaricate* at concentration of 50 ug/ml in well plate method showed 17 mm zone of inhibition against urinary tract pathogen *E.coli* (Sivaraj, Rahman *et al.* 2014). Twenty

microliter of copper nanoparticles of 5–45 nm synthesized using brown alga *Bifurcaria bifurcata* showed inhibition zone of 14 and 16 mm, respectively, against *Enterobacter aerogenes* and *Staphylococcus aureus* (Abboud, Saffaj *et al.* 2014). Copper oxide nanoparticles synthesized by tea leaf or coffee powder extract exhibited inhibition zone of 5–16 mm against *Shigella dysenteriae*, *Vibrio cholerae*, *Streptococcus pneumoniae*, *Staphylococcus aureus* and *E.coli* at concentration from 1 to 200 lg/ disc (Sutradhar, Saha

et al. 2014). Using 40 ml of *Vitis vinifera* synthesized copper nanoparticles showed inhibition zone from 8 to 18 mm against *Bacillus subtilis*, *Escherichia coli*, *Klebsiella pneumoniae*, *Salmonella typhii* and *Staphylococcus aureus* (Angrasan and Subbaiya 2014). Minimum inhibitory concentration of copper nanoparticles ranged from 31.25 to 250 lg/ml against *E.coli*, *Enterococcus faecalis*, *Pseudomonas aeruginosa*, *Shigella flexneri*, *Salmonella typhimurium*, *Proteus vulgaris*, *Staphylococcus aureus* and *Klebsiella Pneumoniae* (Ahamed, Alhadlaq *et al.* 2014). *Gloriosa superba* synthesized copper nanoparticles of 5–10 nm exhibited antibacterial activity against *Klebsiella aerogenes*, *Pseudomonas desmolyticum*, *E.coli* and *Staphylococcus aureus* (Naika, Lingaraju *et al.* 2015).

Using 20 ml of copper nanoparticles of 33 nm synthesized by *Citrus medica* showed inhibitory activity against *E.coli*, *Klebsiella pneumoniae*, *Pseudomonas aeruginosa*, *Propionibacterium acnes* and *Salmonella typhii* (Shende, Ingle *et al.* 2015), while 100 ml of copper nanoparticles of 26.51 nm synthesized using *Garcinia mangostana* at 0.2–1.0 lg/ml concentrations showed antibacterial activity against *E.coli* and *Staphylococcus aureus* (Prabhu, Rao *et al.* 2015). Monodisperse copper nanoparticles of 50 nm have minimum inhibitory concentration ranging between 1.875 and 3.75 lg/ml against standard and clinical strains of *Staphylococcus*, including methicillin resistant *Staphylococcus aureus* and *Candida* species (Kruk, Szczepanowicz *et al.* 2015). Copper oxide nanoparticles of 54 nm synthesized using *Solanum tuberosum* showed minimum inhibitory concentration and minimum bactericidal concentration ranging between 200 and 1000 lg/ml against *Bacillus cereus*, *Enterococcus*, *E.coli*, *Pseudomonas aeruginosa*, *Shigella sonnei* and *Staphylococcus epidermidis* (Alishah, Pourseyedi *et al.* 2017). Good antimicrobial activity shown by copper nanoparticles against the pathogenic bacteria belonging to various genera and species suggests their use as antimicrobial agent. Copper nanoparticles with antimicrobial activity can be employed for the production of a broad range of polymer/ copper Nano

composites to be used in the preparation of antibacterial paints/coatings for application in household, biomedical and aerospace industries. Moreover, copper nanoparticles immobilized into polymer matrix can be employed in the food packaging for retarded deterioration, enhanced shelf life, ensuring good quality and safety of packaged food.

Disease organization by means of copper nanoparticles

Many fungal and bacterial pathogens cause diseases in cultivated crops and thus resulting in yield losses. The antimicrobial activity exhibited by copper nanoparticles against plethora of pathogenic microorganisms (both bacteria and fungi) has piqued the interest in utilization of Cu NPs as agents for disease control in agriculture. Studies carried on *in-vitro* antifungal activity of copper nanoparticles reported the maximal antifungal activity against *Curvularia lunata* MTCC 2030 followed by *Alternaria alternata* MTCC6572, *Fusarium oxysporum* MTCC1755 and *Phoma destructive* DBT66 (Kanhed, Birla *et al.* 2014). Copper nanoparticles manufactured using *Citrus medica* also manifested inhibitory activity against plant pathogenic fungi, *Fusarium culmorum*, *F. oxysporum* and *F. graminearum* (Shende, Ingle *et al.* 2015). In another study, copper nanoparticles displayed maximum antifungal activity against *Fusarium equiseti* with 25 mm zone of inhibition followed by *F. oxysporum* and *F. culmorum* (Bramhanwade, Shende *et al.* 2016). Copper nanoparticles of 20–50 nm at a concentration of 450 ppm could inhibit 93.98% growth of the *Fusarium* specie after 9 days of incubation (Viet, Nguyen *et al.* 2016). Copper-based fungicide has been used in disease inhibition and treatment in many plant species (Borkow and Gabbay 2005). Field studies under protected cultivation using three different copper-based nanoparticles of indistinguishable sizes, i.e. 11–14 nm and shapes, Cu₂O, CuO and Cu/Cu₂O, respectively, against *Phytophthora infestans* on *Lycopersicon esculentum* revealed that copper-based NPs were more efficient than the four registered copper-based agrochemicals. Along with the

propitious potency, it was also found that copper-based nanoparticles did not instigate any irreparable damage/deleterious effect to the plants (Giannousi, Avramidis *et al.* 2013). In exploring copper nanoparticles for disease management, it is just the dawn of an era which has to go long way for safeguarding the plants from disparate diseases in imperishable manner.

Conclusions

Green synthesis of nanoparticles, once considered as an emerging field is a well-established domain of research in nanotechnology with surplus applications. Copper nanoparticles offers a range of applications in medicine, drug delivery, wound dressing, bio labelling, water purification optics, catalysis, structural engineering and several other domains of science and technology. Copper nanoparticles have also been found to have potent antibacterial and antifungal activities and can hence prove to be an effective alternative source to destroy drug resistant microbial species. Due to such diversified range of applications, Copper nanoparticles can prove as suitable and inexpensive alternatives to costly nanoparticles like gold. However, the exact mechanism with which the phytochemicals reduces and stabilizes these nanoparticles is yet to be understood. Complete understanding of this mysterious process will help enable the scientists to use targeted phytochemicals to reduce and cap nanoparticles followed by usage of intentionally designed nanoparticles for specific purposes. This will also help in designing nanoparticles with desired shape and size.

Abbreviations

Cu: Copper, Cu-NPs: Copper Nanoparticles, DLS: Dynamic light scattering, EDAX: Energy dispersive X-ray analysis, EDS: Energy-dispersive spectroscopy, FTIR: Fourier transform infrared spectroscopy, HRTEM: High resolution transmission electron microscopy, NPs: Nanoparticles, UV–VIS: Ultra-violet visible spectroscopy, SEM: Scanning electron microscopy, XRD: X-ray Diffraction, TEM: Transmission electron microscopy.

Acknowledgements

The authors are thankful to Renown Scientist, Dr Bilal Haider Abbasi for his support and courage.

Disclosure statement

No potential conflict of interest was reported by the authors.

References

- Abboud Y, Saffaj A, Chagraoui A, El Bouari, Brouzi O, Tanane, Ihssane B.** 2014. "Biosynthesis, characterization and antimicrobial activity of copper oxide nanoparticles (CONPs) produced using brown alga extract (*Bifurcaria bifurcata*)." *Applied Nanoscience* **4(5)**,571-576.
<http://dx.doi.org/10.1007/s13204-013-0233-x>
- Ahamed M, Alhadlaq HA, KhanM, Karuppiiah P, Al-DhabiNA.** 2014. "Synthesis, characterization, and antimicrobial activity of copper oxide nanoparticles." *Journal of Nanomaterials* **2014**, 17.
<http://dx.doi.org/10.1155/2014/637858>
- Alishah H, PourseyediS, EbrahimipourSY, MahaniSE, RafieiN.** 2017. "Green synthesis of starch-mediated CuO nanoparticles: preparation, characterization, antimicrobial activities and in vitro MTT assay against MCF-7 cell line." *Rendiconti Lincei* **28(1)**,65-71.
<http://dx.doi.org/10.1007/s12210-016-0574-y>
- Aminuzzaman M, KeiLM, LiangWH.** 2017. Green synthesis of copper oxide (CuO) nanoparticles using banana peel extract and their photocatalytic activities. *AIP Conference Proceedings*, AIP Publishing.
<https://doi.org/10.1063/1.4979387>
- Angrasan J, SubbaiyaR.** 2014. "Biosynthesis of copper nanoparticles by *Vitis vinifera* leaf aqueous extract and its antibacterial activity." *International Journal Current Microbiology Applied Science* **3(9)**, 768-774.

- Atarod M, NasrollahzadehM, SajadiSM.** 2015. "Green synthesis of a Cu/reduced graphene oxide/Fe₃O₄ nanocomposite using Euphorbia wallichii leaf extract and its application as a recyclable and heterogeneous catalyst for the reduction of 4-nitrophenol and rhodamine B." RSC Advances **5(111)**, 91532-91543.
<https://doi.org/10.1039/C5RA17269A>
- Athanassiou EK, GrassRN, Stark WJ.** 2006. "Large-scale production of carbon-coated copper nanoparticles for sensor applications." Nanotechnology **17(6)**,1668.
- Awwad A, AlbissB, SalemN.** 2015. "Antibacterial activity of synthesized copper oxide nanoparticles using Malva sylvestris leaf extract." Sikkim Manipal University Medical Journal**2**, 91-101.
- Balogh L, Tomalia DA.** 1998. "Poly (amidoamine) dendrimer-templated nanocomposites. 1. Synthesis of zerovalent copper nanoclusters." Journal of the American Chemical Society **120(29)**,7355-7356.
- Barrabés N, JustJ, Dafinov A, MedinaF, FierroJ, SueirasJ, SalagreP, CesterosY.** 2006. "Catalytic reduction of nitrate on Pt-Cu and Pd-Cu on active carbon using continuous reactor: The effect of copper nanoparticles." Applied Catalysis B: Environmental **62(1)**,77-85.
<https://doi.org/10.1016/j.apcatb.2005.06.015>
- Bordbar M, Z Sharifi-Zarchi and B Khodadadi.** 2017. "Green synthesis of copper oxide nanoparticles/clinoptilolite using Rheum palmatum L. root extract: high catalytic activity for reduction of 4-nitro phenol, rhodamine B, and methylene blue." Journal of Sol-Gel Science and Technology **81(3)**: 724-733.
<https://doi.org/10.1007/s10971-016-4239-1>
- Borkow G, Gabbay J.** 2005. "Copper as a biocidal tool." Current medicinal chemistry **12(18)**: 2163-2175.
- Borkow G, GabbayJ.** 2009. "Copper, an ancient remedy returning to fight microbial, fungal and viral infections." Current Chemical Biology **3(3)**,272-278.
- Bracey CL, Ellis PR HutchingsGJ.** 2009. "Application of copper-gold alloys in catalysis: current status and future perspectives." Chemical Society Reviews **38(8)**,2231-2243.
<https://doi.org/10.1039/B817729P>
- Bramhanwade K, ShendeS, BondeS, GadeA, RaiM.** 2016. "Fungicidal activity of Cu nanoparticles against Fusarium causing crop diseases." Environmental chemistry letters **14(2)**,229-235.
- Carnes CL, Klabunde KJ.** 2003. "The catalytic methanol synthesis over nanoparticle metal oxide catalysts." Journal of Molecular Catalysis A: Chemical **194(1)**,227-236.
[https://doi.org/10.1016/S1381-1169\(02\)00525-3](https://doi.org/10.1016/S1381-1169(02)00525-3)
- Chen Y, WangD, ZhuX, Zheng X, Feng L.** 2012. "Long-term effects of copper nanoparticles on wastewater biological nutrient removal and N₂O generation in the activated sludge process." Environmental science & technology **46(22)**,12452-12458.
<https://doi.org/10.1021/es302646q>
- Chung IM, Abdul RahumanA, MarimuthuS, Vishnu KirthiA, AnbarasanK, Padmini P, RajakumarG.** 2017. "Green synthesis of copper nanoparticles using Eclipta prostrata leaves extract and their antioxidant and cytotoxic activities." Experimental and Therapeutic Medicine.
<https://doi.org/10.3892/etm.2017.4466>
- Cioffi N, TorsiL, Ditaranto N, TantilloG, GhibelliL, Sabbatini L, Bleve-ZacheoT, D'AlessioM, Zambonin PG, TraversaE.** 2005. "Copper nanoparticle/polymer composites with antifungal and bacteriostatic properties." Chemistry of Materials **17(21)**,5255-5262.

- Crooks RM, Zhao M, Sun L, Chechik V, Yeung LK.** 2001. "Dendrimer-encapsulated metal nanoparticles: synthesis, characterization, and applications to catalysis." *Accounts of chemical research* **34(3)**,181-190.
- Devi HS, SinghTD.** 2014. "Synthesis of copper oxide nanoparticles by a novel method and its application in the degradation of methyl orange." *Adv Electron Electr Eng* **4(1)**,83-88.
- Devipriya D, RoopanSM.** 2017. "Cissus quadrangularis mediated ecofriendly synthesis of copper oxide nanoparticles and its antifungal studies against *Aspergillus niger*, *Aspergillus flavus*." *Materials Science and Engineering: C*.
<https://doi.org/10.1016/j.msec.2017.05.130>
- Eastman JA, ChoiS, LiS, YuW, ThompsonL.** 2001. "Anomalously increased effective thermal conductivities of ethylene glycol-based nanofluids containing copper nanoparticles." *Applied physics letters* **78(6)**, 718-720.
- Farias CB, SilvaAF, RufinoRD, LunaJM, SouzaJEG, SarubboLA.** 2014. "Synthesis of silver nanoparticles using a biosurfactant produced in low-cost medium as stabilizing agent." *Electronic Journal of Biotechnology* **17(3)**, 122-125.
- Ghidan AY, Al-AntaryTM, Awwad AM.** 2016. "Green synthesis of copper oxide nanoparticles using *Punica granatum* peels extract: Effect on green peach Aphid." *Environmental Nanotechnology, Monitoring & Management* **6**, 95-98.
<https://doi.org/10.1016/j.enmm.2016.08.002>
- Giannousi K, Avramidis I, Dendrinou-Samara C.** 2013. "Synthesis, characterization and evaluation of copper based nanoparticles as agrochemicals against *Phytophthora infestans*." *RSC Advances* **3(44)**,21743-21752.
<https://doi.org/10.1039/C3RA42118J>
- Gnanavel V, Palanichamy V, RoopanSM.** 2017. "Biosynthesis and characterization of copper oxide nanoparticles and its anticancer activity on human colon cancer cell lines (HCT-116)." *Journal of Photochemistry and Photobiology B: Biology* **171**, 133-138.
<https://doi.org/10.1016/j.jphotobiol.2017.05.001>
- Gopinath M, SubbaiyaR, Selvam MM, SureshD.** 2014. "Synthesis of copper nanoparticles from *Nerium oleander* leaf aqueous extract and its antibacterial activity." *Int J Curr Microbiol Appl Sci* **3(9)**,814-818.
- Guduru RK, Murty KL, Youssef KM, Scattergood RO, Koch CC.** 2007. "Mechanical behavior of nanocrystalline copper." *Materials Science and Engineering: A* **463(1)**,14-21.
- Harne S, SharmaA, DhaygudeM, JoglekarS, KodamK, Hudlikar M.** 2012. "Novel route for rapid biosynthesis of copper nanoparticles using aqueous extract of *Calotropis procera* L. latex and their cytotoxicity on tumor cells." *Colloids and Surfaces B: Biointerfaces* **95**, 284-288.
<https://doi.org/10.1016/j.colsurfb.2012.03.005>
- Hewakuruppu YL, DombrovskyLA, ChenC, Timchenko V, Jiang X, Baek S, TaylorRA.** 2013. "Plasmonic "pump-probe" method to study semi-transparent nanofluids." *Applied optics* **52(24)**, 6041-6050.
- Hoover NN, AutenBJ, ChandlerBD.** 2006. "Tuning supported catalyst reactivity with dendrimer-templated Pt- Cu nanoparticles." *The Journal of Physical Chemistry B* **110(17)**, 8606-8612.
- Husen A, SiddiqiKS.** 2014. "Phytosynthesis of nanoparticles: concept, controversy and application." *Nanoscale research letters* **9(1)**,229.
- Ijaz F, ShahidS, KhanSA, Ahmad W, ZamanS.** 2017. "Green synthesis of copper oxide

nanoparticles using *Abutilon indicum* leaf extract: Antimicrobial, antioxidant and photocatalytic dye degradation activities." *Tropical Journal of Pharmaceutical Research* **16(4)**, 743-753.

<http://dx.doi.org/10.4314/tjpr.v16i4.2>

Iravani S, Zolfaghari B. 2013. "Green synthesis of silver nanoparticles using *Pinus eldarica* bark extract." *BioMed research international* 2013.

Issaabadi Z, Nasrollahzadeh M, Sajadi SM. 2017. "Green synthesis of the copper nanoparticles supported on bentonite and investigation of its catalytic activity." *Journal of Cleaner Production* **142**, 3584-3591.

Jayadrans M, Haneefa MM, Balasubramanian V. 2015. "Green synthesis of copper nanoparticles using natural reducer and stabilizer and an evaluation of antimicrobial activity." *J Chem Pharm Res.* **7**, 251-259.

Jinu U, Gomathi M, Saiqa I, Geetha N, Benelli G, Venkatachalam P. 2017. "Green engineered biomolecule-capped silver and copper nanohybrids using *Prosopis cineraria* leaf extract: Enhanced antibacterial activity against microbial pathogens of public health relevance and cytotoxicity on human breast cancer cells (MCF-7)." *Microbial Pathogenesis* **105**, 86-95.

<https://doi.org/10.1016/j.micpath.2017.02.019>

Kala A, Soosairaj S, Mathiyazhagan S, Raja P. 2016. "Green synthesis of copper bionanoparticles to control the bacterial leaf blight disease of rice." *Current Science (00113891)* **110(10)**.

Kamal T, Khan SB, Asiri AM. 2016. "Synthesis of zero-valent Cu nanoparticles in the chitosan coating layer on cellulose microfibrils: evaluation of azo dyes catalytic reduction." *Cellulose* **23(3)**, 1911-1923.

Kang X, Mai Z, Zou X, Cai P, Mo J. 2007. "A sensitive nonenzymatic glucose sensor in alkaline media with a copper nanocluster/multiwall carbon

nanotube-modified glassy carbon electrode." *Analytical biochemistry* **363(1)**, 143-150.

<https://doi.org/10.1016/j.ab.2007.01.003>

Kanhed P, Birla S, Gaikwad S, Gade A, BSeabra A, Rubilar O, Duran N, Rai M. 2014. "In vitro antifungal efficacy of copper nanoparticles against selected crop pathogenic fungi." *Materials Letters* **115**, 13-17.

<https://doi.org/10.1016/j.matlet.2013.10.011>

Kantam ML, Jaya VS, Lakshmi MJ, Reddy BR, Choudary B, Bhargava S. 2007. "Alumina supported copper nanoparticles for aziridination and cyclopropanation reactions." *Catalysis Communications* **8(12)**, 1963-1968.

Kaviya S, Santhanalakshmi J, Viswanathan B. 2011. "Green synthesis of silver nanoparticles using *Polyalthia longifolia* leaf extract along with D-sorbitol: study of antibacterial activity." *Journal of nanotechnology* **2011**.

Kim MH, Li, Lee EP, Xia Y. 2008. "Polyol synthesis of Cu₂O nanoparticles: use of chloride to promote the formation of a cubic morphology." *Journal of Materials Chemistry* **18(34)**, 4069-4073.

<https://doi.org/10.1039/B805913F>

Kruk T, Szczepanowicz K, Stefańska J, Socha RP, Warszyński P. 2015. "Synthesis and antimicrobial activity of monodisperse copper nanoparticles." *Colloids and Surfaces B: Biointerfaces* **128**, 17-22.

<https://doi.org/10.1016/j.colsurfb.2015.02.009>

Kumar B, Smita K, Cumbal L, Debut A, Angulo Y. 2015. "Biofabrication of copper oxide nanoparticles using Andean blackberry (*Rubus glaucus* Benth.) fruit and leaf." *Journal of Saudi Chemical Society*.

Kumar PV, Shameem U, Kollu P, Kalyani R, Pammi S. 2015. "Green synthesis of copper oxide nanoparticles using *Aloe vera* leaf extract and its

antibacterial activity against fish bacterial pathogens." *BioNanoScience* **5**(3), 135-139.

Kuppusamy P, IlavenilS, SrigopalramS, Maniam GP, Yusoff MM, Govindan N, Choi KC. 2017. "Treating of palm oil mill effluent using *Commelina nudiflora* mediated copper nanoparticles as a novel bio-control agent." *Journal of Cleaner Production* **141**, 1023-1029.

Lee HJ, Song JY, KimBS. 2013. "Biological synthesis of copper nanoparticles using *Magnolia kobus* leaf extract and their antibacterial activity." *Journal of Chemical Technology and Biotechnology* **88**(11), 1971-1977.

Leong MK. 2016. *Green Synthesis, Characterization of Copper (II) Oxide Nanoparticles and Their Photocatalytic Activity*, UTAR.

Li CH, Peterson G. 2006. "Experimental investigation of temperature and volume fraction variations on the effective thermal conductivity of nanoparticle suspensions (nanofluids)." *Journal of Applied Physics* **99**(8): 084314.
<https://doi.org/10.1063/1.2191571>

Li Y, Liang J, Tao Z, Chen J. 2008. "CuO particles and plates: synthesis and gas-sensor application." *Materials Research Bulletin* **43**(8), 2380-2385.

Li Z, Lee D, Sheng X, Cohen RE, Rubner MF. 2006. "Two-level antibacterial coating with both release-killing and contact-killing capabilities." *Langmuir* **22**(24), 9820-9823.

Lin YSE, Vidic RD, Stout JE, Victor LY. 1996. "Individual and combined effects of copper and silver ions on inactivation of *Legionella pneumophila*." *Water Research* **30**(8), 1905-1913.

Longano D, Ditaranto N, Cioffi N, Di Niso F, Sibillano T, Ancona A, Conte A, Del Nobile M, Sabbatini L, Torsi L. 2012. "Analytical

characterization of laser-generated copper nanoparticles for antibacterial composite food packaging." *Analytical and bioanalytical chemistry* **403**(4), 1179-1186.

Lu L, Sui M, Lu K. 2001. "Cold rolling of bulk nanocrystalline copper." *Acta materialia* **49**(19), 4127-4134.
[https://doi.org/10.1016/S1359-6454\(01\)00248-8](https://doi.org/10.1016/S1359-6454(01)00248-8)

Male KB, Hrapovic S, Liu Y, Wang D, Luong JH. 2004. "Electrochemical detection of carbohydrates using copper nanoparticles and carbon nanotubes." *Analytica Chimica Acta* **516**(1), 35-41.
<https://doi.org/10.1016/j.aca.2004.03.075>

Mandal D, Bolander ME, MukhopadhyayD, SarkarG, MukherjeeP. 2006. "The use of microorganisms for the formation of metal nanoparticles and their application." *Applied microbiology and biotechnology* **69**(5), 485-492.
<https://doi.org/10.1007/s00253-005-0179-3>

Mittal AK, Chisti Y, BanerjeeUC. 2013. "Synthesis of metallic nanoparticles using plant extracts." *Biotechnology advances* **31**(2), 346-356.

Momeni SS, Nasrollahzadeh M, RustaiyanA. 2016. "Green synthesis of the Cu/ZnO nanoparticles mediated by *Euphorbia prolifera* leaf extract and investigation of their catalytic activity." *Journal of colloid and interface science* **472**, 173-179.
<https://doi.org/10.1016/j.jcis.2016.03.042>

Nagajyothi P, MuthuramanP, Sreekanth T, KimDH, Shim J. 2017. "Green synthesis: In-vitro anticancer activity of copper oxide nanoparticles against human cervical carcinoma cells." *Arabian Journal of Chemistry* **10**(2), 215-225.
<https://doi.org/10.1016/j.arabjch.2016.01.011>

Naika HR, LingarajuK, Manjunath K, Kumar D, Nagaraju G, Suresh D, Nagabhushana H. 2015. "Green synthesis of CuO nanoparticles using *Gloriosa superba* L. extract and their antibacterial

activity." *Journal of Taibah University for Science* **9(1)**, 7-12.

Narayanan R, El-Sayed MA. 2004. "Effect of nanocatalysis in colloidal solution on the tetrahedral and cubic nanoparticle shape: Electron-transfer reaction catalyzed by platinum nanoparticles." *The Journal of Physical Chemistry B* **108(18)**, 5726-5733.

Nasrollahzadeh M, Maham M, Sajadi SM. 2015. "Green synthesis of CuO nanoparticles by aqueous extract of *Gundelia tournefortii* and evaluation of their catalytic activity for the synthesis of N-monosubstituted ureas and reduction of 4-nitrophenol." *Journal of colloid and interface science* **455**, 245-253.

<https://doi.org/10.1016/j.jcis.2015.05.045>

Nasrollahzadeh M, Sajadi SM, Khalaj M. 2014. "Green synthesis of copper nanoparticles using aqueous extract of the leaves of *Euphorbia esula* L and their catalytic activity for ligand-free Ullmann-coupling reaction and reduction of 4-nitrophenol." *RSC Advances* **4(88)**, 47313-47318.

<https://doi.org/10.1039/C4RA08863H>

Nasrollahzadeh M, Sajadi SM, Rostami-Vartooni A, Khalaj M. 2015. "Natrolite zeolite supported copper nanoparticles as an efficient heterogeneous catalyst for the 1, 3-dipolar cycloaddition and cyanation of aryl iodides under ligand-free conditions." *Journal of colloid and interface science* **453**, 237-243.

<https://doi.org/10.1016/j.jcis.2015.04.047>

Niu Y, RM Crooks. 2003. "Dendrimer-encapsulated metal nanoparticles and their applications to catalysis." *Comptes Rendus Chimie* **6(8)**, 1049-1059.

Pecharromán C, Esteban-Cubillo A, Montero I, Moya JS, Aguilar E, Santarén J, Alvarez A. 2006. "Monodisperse and Corrosion-Resistant Metallic Nanoparticles Embedded into Sepiolite Particles for Optical and Magnetic Applications."

Journal of the American Ceramic Society **89(10)**, 3043-3049.

Pedersen DB, Wang S, Liang SH. 2008. "Charge-Transfer-Driven Diffusion Processes in Cu@ Cu-Oxide Core-Shell Nanoparticles: Oxidation of 3.0±0.3 nm Diameter Copper Nanoparticles." *The Journal of Physical Chemistry C* **112(24)**, 8819-8826.

Petit C, Lixon P, Pileni MP. 1993. "In situ synthesis of silver nanocluster in AOT reverse micelles." *The Journal of Physical Chemistry* **97(49)**, 12974-12983.

Phong NTP, Khuong VQ, Tho TD, Van Du C, Minh NH. 2011. "Green synthesis of copper nanoparticles colloidal solutions and used as pink disease treatment drug for rubber tree." *Proceedings of IWNA* **288**, 10-12.

Prabhu Y, Rao KV, Sai VS, Pavani T. 2015. "A facile biosynthesis of copper nanoparticles: a micro-structural and antibacterial activity investigation." *Journal of Saudi Chemical Society*.

Prasad KS, Patra A, Shruthi G, Chandan S. 2017. "Aqueous Extract of *Saracai indica* Leaves in the Synthesis of Copper Oxide Nanoparticles: Finding a Way towards Going Green." *Journal of Nanotechnology* **2017**.

<https://doi.org/10.1155/2017/7502610>

Prasad PR, Kanchi S, Naidoo E. 2016. "In-vitro evaluation of copper nanoparticles cytotoxicity on prostate cancer cell lines and their antioxidant, sensing and catalytic activity: One-pot green approach." *Journal of Photochemistry and Photobiology B: Biology* **161**, 375-382.

<https://doi.org/10.1016/j.jphotobiol.2016.06.008>

Rafique M, Shaikh AJ, Rasheed R, Tahi MB, Bakhat HF, Rafique MS, Rabbani F. 2017. "A review on synthesis, characterization and applications of copper nanoparticles using green method." *Nano* **12(04)**, 1750043.

- Ramyadevi J, Jeyasubramanian K, Marikani A, Rajakumar G, Rahuman AA.** 2012. "Synthesis and antimicrobial activity of copper nanoparticles." *Materials letters* **71**, 114-116.
<http://dx.doi.org/10.1016/j.matlet.2011.12.055>
- Raveendran P, Fu J, Wallen SL.** 2003. "Completely "green" synthesis and stabilization of metal nanoparticles." *Journal of the American Chemical Society* **125(46)**, 13940-13941.
- Ren G, Hu D, Cheng EW, Vargas-Reus MA, Reip P, Allaker RP.** 2009. "Characterisation of copper oxide nanoparticles for antimicrobial applications." *International journal of antimicrobial agents* **33(6)**, 587-590.
- Rodriguez JA, Liu P, Hrbek J, Evans, Perez M.** 2007. "Water Gas Shift Reaction on Cu and Au Nanoparticles Supported on CeO₂ (111) and ZnO (000 $\bar{1}$): Intrinsic Activity and Importance of Support Interactions." *Angewandte Chemie International Edition* **46(8)**, 1329-1332.
- Rosbero TMS, DH Camacho.** 2017. "Green preparation and characterization of tentacle-like silver/copper nanoparticles for catalytic degradation of toxic chlorpyrifos in water." *Journal of Environmental Chemical Engineering*.
<http://dx.doi.org/10.1016/j.jece.2017.05.009>
- Rubilar O, Rai M, Tortella G, Diez MC, Seabra AB, Durán N.** 2013. "Biogenic nanoparticles: copper, copper oxides, copper sulphides, complex copper nanostructures and their applications." *Biotechnology letters* **35(9)**, 1365-1375.
- Sadanand V, Rajini N, Rajulu AV, Satyanarayana B.** 2016. "Preparation of cellulose composites with in situ generated copper nanoparticles using leaf extract and their properties." *Carbohydrate polymers* **150**: 32-39.
<http://dx.doi.org/10.1016/j.carbpol.2016.04.121>
- Salavati-Niasari M, Davar F, Mir N.** 2008. "Synthesis and characterization of metallic copper nanoparticles via thermal decomposition." *Polyhedron* **27(17)**, 3514-3518.
- Saranyaadevi K, Subha V, Ravindran RE, Renganathan S.** 2014. "Synthesis and characterization of copper nanoparticle using Capparis zeylanica leaf extract." *Int J ChemTech Res* **6(10)**, 4533-4541.
- Schilling K, Bradford B, Castelli D, Dufour E, Nash JF, Pape W, Schulte S, Tooley I, van den Bosch J, Schellauff.** 2010. "Human safety review of "nano" titanium dioxide and zinc oxide." *Photochemical & Photobiological Sciences* **9(4)**, 495-509.
<http://dx.doi.org/10.1039/B9PP00180H>
- Shende S, Ingle AP, Gade A, Rai M.** 2015. "Green synthesis of copper nanoparticles by Citrus medica Linn. (Idilimbu) juice and its antimicrobial activity." *World Journal of Microbiology and Biotechnology* **31(6)**, 865-873.
- Shi LB, Tang PF, Zhang W, Zhao YP, Zhang LC, Zhang H.** 2017. "Green synthesis of CuO nanoparticles using Cassia auriculata leaf extract and in vitro evaluation of their biocompatibility with rheumatoid arthritis macrophages (RAW 264.7)." *Tropical Journal of Pharmaceutical Research* **16(1)**, 185-192.
<http://dx.doi.org/10.4314/tjpr.v16i1.25>
- Shobha G, Moses V, nanda S A.** 2014. "Biological Synthesis of Copper Nanoparticles and its impact." *International Journal of Pharmaceutical Science Invention* **3(8)**, 2319-6718.
- Singh S, Kumar N, Kumar M, Agarwal A, Mizaikoff B.** 2017. "Electrochemical sensing and remediation of 4-nitrophenol using bio-synthesized copper oxide nanoparticles." *Chemical Engineering Journal* **313**, 283-292.

- Sivaraj R, RahmanPK, RajivP, Salam HA, VenkateshR.** 2014. "Biogenic copper oxide nanoparticles synthesis using Tabernaemontana divaricate leaf extract and its antibacterial activity against urinary tract pathogen." *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* **133**, 178-181.
<http://dx.doi.org/10.1016/j.saa.2014.05.048>
- Song L, Vijver MG, PeijnenburgWJ.** 2015. "Comparative toxicity of copper nanoparticles across three Lemnaceae species." *Science of the Total Environment* **518**, 217-224.
- Subhankari I, NayakP.** 2013. "Synthesis of copper nanoparticles using *Syzygium aromaticum* (Cloves) aqueous extract by using green chemistry." *World J Nano Sci Technol* **2**(1): 14-17.
- Supradhar P, Saha M, MaitiD.** 2014. "Microwave synthesis of copper oxide nanoparticles using tea leaf and coffee powder extracts and its antibacterial activity." *Journal of Nanostructure in Chemistry* **4**(1), 86.
- Swarnkar R, Singh S, GopalR.** 2011. "Effect of aging on copper nanoparticles synthesized by pulsed laser ablation in water: structural and optical characterizations." *Bulletin of Materials Science* **34**(7),1363-1369.
- Thakkar KN, MhatreSS, ParikhRY.** 2010. "Biological synthesis of metallic nanoparticles." *Nanomedicine: Nanotechnology, Biology and Medicine* **6**(2),257-262.
<http://dx.doi.org/10.1016/j.nano.2009.07.002>
- Thirumurugan A, HarshiniE, MarakathanandhiniBD, Kannan SR MuthukumarP.** 2017. Catalytic Degradation of Reactive Red 120 by Copper Oxide Nanoparticles Synthesized by *Azadirachta indica*. *Bioremediation and Sustainable Technologies for Cleaner Environment*, Springer: 95-102.
- Vanathi P, Rajiv P, Sivaraj R.** 2016. "Synthesis and characterization of Eichhornia-mediated copper oxide nanoparticles and assessing their antifungal activity against plant pathogens." *Bulletin of Materials Science* **39**(5),1165-1170.
- Viet P V, Nguyen HT, Cao TM, Hieu LV.** 2016. "Fusarium antifungal activities of copper nanoparticles synthesized by a chemical reduction method." *Journal of Nanomaterials* **2016**, 6.
<http://dx.doi.org/10.1155/2016/1957612>
- Vukojević S, Trapp O, Grunwaldt JD, Kiener CF, Schüth.** 2005. "Quasi-homogeneous methanol synthesis over highly active copper nanoparticles." *Angewandte Chemie* **117**(48), 8192-8195.
- Wali M, Sajjad A, Sumaira S.** 2017. "Green Synthesis of Gold Nanoparticles and Their Characterizations Using Plant Extract of *Papaver somniferum*." *Nano Sci Nano Technol* **11**(2), 118.
- Wang Y, Chen M, Zhou F, Ma E.** 2002. "High tensile ductility in a nanostructured metal." *Nature* **419**(6910), 912.
- Wu D, Wang W, He X, Jiang M, Lai C, Hu X, Wang M, Xi J.** 2017. "Biofabrication of nano copper oxide and its aptamer bioconjugate for delivery of mRNA 29b to lung cancer cells." *Materials Science and Engineering: C*.
<http://dx.doi.org/10.1016/j.msec.2017.04.081>
- Xu Q, Zhao Y, Xu JZ, Zhu JJ.** 2006. "Preparation of functionalized copper nanoparticles and fabrication of a glucose sensor." *Sensors and Actuators B: Chemical* **114**(1), 379-386.
- Yin M, Wu CK, Lou Y, Burda C, Koberstein JT, Zhu Y, O'Brien S.** 2005. "Copper oxide nanocrystals." *Journal of the American Chemical Society* **127**(26), 9506-9511.
- Yoon KY, Byeon JH, Park JH Hwang J.** 2007. "Susceptibility constants of *Escherichia coli* and

Bacillus subtilis to silver and copper nanoparticles." *Science of the Total Environment* **373(2)**, 572-575.

Yu-sen EL, Vidic R D, Stout JE, McCartney C A, Victor LY. 1998. "Inactivation of Mycobacterium avium by copper and silver ions." *Water Research* **32(7)**, 1997-2000.

Yuhua BD, YangP. 2009. "Nanowire-based all-oxide solar cells." *Journal of the American Chemical Society* **131(10)**, 3756-3761.

Zain NM, Stapley A, ShamaG. 2014. "Green synthesis of silver and copper nanoparticles using Ascorbic acid and Chitosan for antimicrobial applications." *Carbohydrate polymers* **112**, 195-202.
<http://dx.doi.org/10.1016/j.carbpol.2014.05.081>